

CYCOLOY™ RESIN XCM830

REGION EUROPE

DESCRIPTION

CYCOLOY™ XCM830 resin is a 8% Talc filled a polycarbonate / acrylonitrile butadiene styrene (PC/ABS). High stiffness and impact performance

TYPICAL PROPERTY VALUES

Revision 20250414

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	60	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	55	MPa	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	5	%	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	100	%	ASTM D638
Tensile Modulus, 5 mm/min	3400	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	95	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	3100	MPa	ASTM D790
Tensile Stress, yield, 5 mm/min	56	MPa	ISO 527
Tensile Stress, break, 5 mm/min	55	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	5	%	ISO 527
Tensile Strain, break, 5 mm/min	100	%	ISO 527
Tensile Modulus, 1 mm/min	3100	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	95	MPa	ISO 178
Flexural Modulus, 2 mm/min	3100	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	500	J/m	ASTM D256
Izod Impact, notched, -30°C	120	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	65	J	ASTM D3763
Izod Impact, unnotched 80*10*4 +23°C	NB	kJ/m²	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	NB	kJ/m²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	40	kJ/m²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	10	kJ/m²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	45	kJ/m²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	10	kJ/m²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	NB	kJ/m²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*4 sp=62mm	NB	kJ/m²	ISO 179/1eU
THERMAL			
Vicat Softening Temp, Rate B/50	138	°C	ASTM D1525
HDT, 1.82 MPa, 3.2mm, unannealed	118	°C	ASTM D648
CTE, -40°C to 40°C, flow	6.E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	7.E-05	1/°C	ASTM E831
Thermal Conductivity	0.2	W/m·°C	ISO 8302
CTE, -40°C to 40°C, flow	6.E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	7.E-05	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Vicat Softening Temp, Rate B/50	138	°C	ISO 306
Vicat Softening Temp, Rate B/120	140	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	118	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.22	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm	0.7 – 0.8	%	SABIC method
Melt Flow Rate, 260°C/5.0 kgf	11	g/10 min	ASTM D1238
Density	1.22	g/cm ³	ISO 1183
Water Absorption, (23°C/saturated)	0.4	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.1	%	ISO 62
Melt Volume Rate, MVR at 260°C/5.0 kg	9	cm ³ /10 min	ISO 1133
INJECTION MOLDING			
Drying Temperature	120 – 110	°C	
Drying Time	2 – 6	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	270 – 300	°C	
Nozzle Temperature	260 – 290	°C	
Front - Zone 3 Temperature	270 – 300	°C	
Middle - Zone 2 Temperature	265 – 290	°C	
Rear - Zone 1 Temperature	260 – 270	°C	
Mold Temperature	60 – 100	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	30 – 80	%	
Vent Depth	0.038 – 0.076	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.