

Apec® 1795

Easy-flow grades / easy-release

MVR (330°C/2.16kg) 30 cm³/10 min; easy release; low viscosity; 'softening temperature (VST/B 120)=173°C; injection molding - melt temperature 320 - 340°C; Covers for brake lights and indicator lights; Headlamp reflectors/bezels

ISO Shortname

PC-HT

Property	Test Condition	Unit	Standard	typical Value
Rheological properties				
C Melt volume-flow rate	330 °C/ 2.16 kg	cm³/10 min	ISO 1133	30
C Melt mass-flow rate	330 °C/ 2.16 kg	g/10 min	ISO 1133	31
C Molding shrinkage, parallel	60x60x2 mm³	%	ISO 294-4	0.8
C Molding shrinkage, normal	60x60x2 mm³	%	ISO 294-4	0.8
Mechanical properties (23 °C/50 % r. h.)				
C Tensile modulus	1 mm/min	MPa	ISO 527-1,-2	2350
C Yield stress	50 mm/min	MPa	ISO 527-1,-2	71
C Yield strain	50 mm/min	%	ISO 527-1,-2	6.6
C Nominal strain at break	50 mm/min	%	ISO 527-1,-2	> 50
C Charpy impact strength	23 °C	kJ/m²	ISO 179/1eU	N
C Charpy impact strength	-30 °C	kJ/m²	ISO 179/1eU	N
C Flexural modulus	2 mm/min	MPa	ISO 178	2400
C Flexural strength	2 mm/min	MPa	ISO 178	105
C Ball indentation hardness		N/mm²	ISO 2039-1	125
Thermal properties				
C Temperature of deflection under load	1.80 MPa	°C	ISO 75-1,-2	148
C Temperature of deflection under load	0.45 MPa	°C	ISO 75-1,-2	162
C Vicat softening temperature	50 N; 120 °C/h	°C	ISO 306	173
C Relative temperature index (Tensile strength)		°C	UL 746B	140
C Relative temperature index (Tensile impact strength)		°C	UL 746B	130
C Relative temperature index (Electric strength)		°C	UL 746B	140
C Coefficient of linear thermal expansion, parallel	23 to 55 °C	10 ⁻⁴ /K	ISO 11359-1,-2	0.65
C Coefficient of linear thermal expansion, normal	23 to 55 °C	10 ⁻⁴ /K	ISO 11359-1,-2	0.65
C Burning behavior UL 94 (1.5 mm)	1.5 mm	Class	UL 94	HB
C Oxygen index	Method A	%	ISO 4589-2	25
C Glow wire test (GWFI)		°C	IEC 60695-2-12	850
Electrical properties (23 °C/50 % r. h.)				
C Relative permittivity	100 Hz	-	IEC 60250	3
C Relative permittivity	1 MHz	-	IEC 60250	2,9
C Dissipation factor	100 Hz	10 ⁻⁴	IEC 60250	10
C Dissipation factor	1 MHz	10 ⁻⁴	IEC 60250	80
C Volume resistivity		Ohm·m	IEC 62631-3-1	1E15
C Surface resistivity		Ohm	IEC 62631-3-2	1E16
C Electrical strength	1 mm	kV/mm	IEC 60243-1	35
C Comparative tracking index CTI	Solution A	Rating	IEC 60112	250
C Comparative tracking index CTI M	Solution B	Rating	IEC 60112	125
C Electrolytic corrosion		Rating	IEC 60426	A1
Other properties (23 °C)				
C Water absorption (saturation value)	Water at 23 °C	%	ISO 62	0.3
C Water absorption (equilibrium value)	23 °C; 50 % r. h.	%	ISO 62	0.12
C Density		kg/m³	ISO 1183-1	1170
Material specific properties				
C Refractive index	Procedure A	-	ISO 489	1.576
C Luminous transmittance (clear transparent materials)	1 mm	%	ISO 13468-2	89

Apec® 1795

Property	Test Condition	Unit	Standard	typical Value
Processing conditions for test specimens				
C Injection molding - Melt temperature		°C	ISO 294	330
C Injection molding - Mold temperature		°C	ISO 294	100
C Injection molding - Injection velocity		mm/s	ISO 294	200
Recommended processing and drying conditions				
Melt temperatures		°C	-	320 - 340
Standard Melt temperature		°C	-	330
Barrel Temperatures - Rear		°C	-	290 - 300
Barrel Temperatures - Middle		°C	-	300 - 310
Barrel Temperatures - Front		°C	-	310 - 320
Barrel Temperatures - Nozzle		°C	-	320 - 330
Mold Temperatures		°C	-	110 - 130
Hold Pressure (% of injection pressure)		%	-	50 - 75
Plastic Back Pressure (specific)		bar	-	50 - 150
Peripheral Screw Speed		m/s	-	0.05 - 0.2
Shot-to-Cylinder Size		%	-	30 - 70
Dry Air Drying Temperature		°C	-	130
Dry Air Drying Time		h	-	2-3
Moisture Content max. (%)		%	-	<= 0,02
Vent Depth		mm	-	0.025 - 0.075

C These property characteristics are taken from the CAMPUS plastics data bank and are based on the international catalogue of basic data for plastics according to ISO 10350.

Impact properties: N = non-break, P = partial break, C = complete break

Apec® 1795

Disclaimer

Typical value

These values are typical values only. Unless explicitly agreed in written form, they do not constitute a binding material specification or warranted values. Values may be affected by the design of the mold/die, the processing conditions and coloring/pigmentation of the product. Unless specified to the contrary, the property values given have been established on standardized test specimens at room temperature.

General

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations are beyond our control. Therefore, it is imperative that you test our products, technical assistance, information and recommendations to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by Covestro. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent. With respect to health, safety and environment precautions, the relevant Material Safety Data Sheets (MSDS) and product labels must be observed prior to working with our products.

Non Medical and non Food Contact Grade

This product is not designated for the manufacture of a pharmaceutical/medicinal product, medical device or of intermediate products for medical devices¹). This product is also not registered for Covestro for the use in other specifically regulated applications, in particular applications requiring regulatory registration, approval or notification (e.g. including cosmetics, plant protection, food processing, food contact and others). If the intended use of the product is for the manufacture of a pharmaceutical, medical device or of intermediate products for medical devices or for other specifically regulated applications which may lead to a regulatory obligation of Covestro, Covestro must be contacted in advance to provide its agreement to sell such product for such purpose. Nonetheless, any determination as to whether a product is appropriate for use in a pharmaceutical, medical device or intermediate products for medical devices or for the use in other specifically regulated applications, must be made solely by the purchaser of the product without relying upon any representations by Covestro, irrespective of the existence of any regulatory obligation for the registration, approval or notification. 1) Please see the "Guidance on Use of Covestro Products in a Medical Application" document.

Recommended Processing and Drying Conditions

Barrel temperatures are valid for a standard 3-zone barrel. Temperature set-up for different barrel types may change according to configuration. Values for hold pressure as percentage of injection pressure may vary depending on, amongst others, part geometry, injection molding machine and injection mold. Drying conditions are for dry air dryers only. Drying times and drying temperatures may differ depending on valid dryer type. Further information is provided by your local Covestro support as well as in the following brochures: Injection Molding of High Quality Molded Parts - Drying; Determining the Dryness of Makrolon by TVI Test; The fundamentals of shrinkage in thermoplastics; Shrinkage and deformation of glass fiber reinforced thermoplastics [...]. <https://www.plastics.covestro.com/Library/Overview.aspx>

Covestro AG
Kaiser-Wilhelm-Allee 60
51373 Leverkusen
Germany
www.solutions.covestro.com