

Bayblend® M303 FR

FR grades / Non reinforced

(PC+ABS)-Blend; Vicat/B 120 temperature = 115°C; suitable for use in electrical and electronic devices; Manufactured according to GMP; tested only according to ISO 10993-5 and ISO 10993-10 for contact with uncompromised skin only; for questions regarding biocompatibility we ask for an email inquiry under plastics@covestro.com

ISO Shortname

PC+ABS-FR(40)

Property	Test Condition	Unit	Standard	typical Value
Rheological properties				
C Melt volume-flow rate	260 °C/ 5 kg	cm ³ /10 min	ISO 1133	11
C Melt viscosity	1000 s ⁻¹ / 260 °C	Pa·s	b.o. ISO 11443-A	410
C Molding shrinkage, parallel/normal	Value range based on general practical experience	%	b.o. ISO 2577	0.5 - 0.7
Mechanical properties (23 °C/50 % r. h.)				
C Tensile modulus	1 mm/min	MPa	ISO 527-1,-2	2650
C Yield stress	50 mm/min	MPa	ISO 527-1,-2	69
C Yield strain	50 mm/min	%	ISO 527-1,-2	5
C Nominal strain at break	50 mm/min	%	ISO 527-1,-2	> 50
C Stress at break	50 mm/min	MPa	ISO 527-1,-2	53
C Izod impact strength	23 °C	kJ/m ²	ISO 180/U	N
C Izod notched impact strength	23 °C	kJ/m ²	ISO 180/A	40
C Izod notched impact strength	-30 °C	kJ/m ²	ISO 180/A	10
Thermal properties				
C Temperature of deflection under load	1.80 MPa	°C	ISO 75-1,-2	98
C Temperature of deflection under load	0.45 MPa	°C	ISO 75-1,-2	106
C Vicat softening temperature	50 N; 50 °C/h	°C	ISO 306	113
C Vicat softening temperature	50 N; 120 °C/h	°C	ISO 306	115
C Coefficient of linear thermal expansion, parallel	23 to 55 °C	10 ⁻⁴ /K	ISO 11359-1,-2	0.68
C Coefficient of linear thermal expansion, normal	23 to 55 °C	10 ⁻⁴ /K	ISO 11359-1,-2	0.72
C Burning behavior UL 94 (1.5 mm) [UL recognition]	1.5 mm	Class	UL 94	V-0
C Burning behavior UL 94 [UL recognition]	0.75 mm	Class	UL 94	V-2
Electrical properties (23 °C/50 % r. h.)				
C Relative permittivity	100 Hz	-	IEC 60250	3.2
C Relative permittivity	1 MHz	-	IEC 60250	3.1
C Dissipation factor	100 Hz	10 ⁻⁴	IEC 60250	37
C Dissipation factor	1 MHz	10 ⁻⁴	IEC 60250	75
C Volume resistivity		Ohm·m	IEC 62631-3-1	1E15
C Surface resistivity		Ohm	IEC 62631-3-2	1E17
C Electrical strength	1 mm	kV/mm	IEC 60243-1	35
Other properties (23 °C)				
C Water absorption (saturation value)	Water at 23 °C	%	ISO 62	0.5
C Density		kg/m ³	ISO 1183-1	1190

Bayblend® M303 FR

Property	Test Condition	Unit	Standard	typical Value
Recommended processing and drying conditions				
Melt temperatures		°C	-	240 - 270
Standard Melt temperature		°C	-	260
Barrel Temperatures - Rear		°C	-	220 - 230
Barrel Temperatures - Middle		°C	-	225 - 235
Barrel Temperatures - Front		°C	-	230 - 240
Barrel Temperatures - Nozzle		°C	-	255 - 265
Mold Temperatures		°C	-	60 - 90
Hold Pressure (% of injection pressure)		%	-	50 - 75
Plastic Back Pressure (specific)		bar	-	50 - 150
Peripheral Screw Speed		m/s	-	0.05 - 0.2
Shot-to-Cylinder Size		%	-	30 - 70
Dry Air Drying Temperature		°C	-	80
Dry Air Drying Time		h	-	4
Moisture Content max. (%)		%	-	<= 0,02
Vent Depth		mm	-	0.025 - 0.075

C These property characteristics are taken from the CAMPUS plastics data bank and are based on the international catalogue of basic data for plastics according to ISO 10350.

Impact properties: N = non-break, P = partial break, C = complete break

Bayblend® M303 FR

Disclaimer

Typical value

These values are typical values only. Unless explicitly agreed in written form, they do not constitute a binding material specification or warranted values. Values may be affected by the design of the mold/die, the processing conditions and coloring/pigmentation of the product. Unless specified to the contrary, the property values given have been established on standardized test specimens at room temperature.

General

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations are beyond our control. Therefore, it is imperative that you test our products, technical assistance, information and recommendations to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by Covestro. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent. With respect to health, safety and environment precautions, the relevant Material Safety Data Sheets (MSDS) and product labels must be observed prior to working with our products.

Medical Grade with limited bio-compatibility

The biocompatibility testing referenced above cannot assure the biocompatibility of final or intermediate products made from Covestro products or the suitability of such products for their use in a medical application, i.e., the test data cannot be used to conclude that any medical devices manufactured from the Covestro products meet the necessary requirements of ISO Standard 10993-1. It is the sole responsibility of the manufacturer of the final end-use product to conduct all necessary tests (including biocompatibility tests) and inspections and to evaluate the final product under actual end-use requirements. For more information on Covestro products in medical applications, please request from your sales support contact our Guidance document: Guidance on Use of Covestro Products in a Medical Application

Recommended Processing and Drying Conditions

Barrel temperatures are valid for a standard 3-zone barrel. Temperature set-up for different barrel types may change according to configuration. Values for hold pressure as percentage of injection pressure may vary depending on, amongst others, part geometry, injection molding machine and injection mold. Drying conditions are for dry air dryers only. Drying times and drying temperatures may differ depending on valid dryer type. Further information is provided by your local Covestro support as well as in the following brochures: Injection Molding of High Quality Molded Parts - Drying; Determining the Dryness of Makrolon by TVI Test; The fundamentals of shrinkage in thermoplastics; Shrinkage and deformation of glass fiber reinforced thermoplastics [...]. <https://www.plastics.covestro.com/Library/Overview.aspx>

Disclaimer shrinkage data

Shrinkage data is provided as a reference only, and is based on sample plaques molded under specific, controlled processing conditions. Shrinkage rates in production parts can vary and are influenced by several variables such as, but not limited to: part design (e.g. part size, thickness and geometry), mold design (e.g. gate type and location, runner design, mold materials, cooling system), molding conditions (e.g. processing temperature, mold temperature, packing time and pressure, injection speed). We suggest materials be evaluated in existing applicable molds to achieve the most accurate shrinkage estimation for your specific application and processing practices. The final choice of shrinkage is the responsibility of the user of the material, and should be made based on your experience and testing results. We shall not be liable for any damage caused by the use of the shrinkage data as provided by us. If you have any questions, pls consult technical representatives from Covestro.

Covestro AG
Kaiser-Wilhelm-Allee 60
51373 Leverkusen
Germany
www.solutions.covestro.com