

LEXANT™ RESIN LUX2289

REGION AMERICAS

DESCRIPTION

LEXANT™ LUX2289 resin is a 17 MFR polycarbonate, MVR of 16. UV stabilized. UL94 V2 rated. High light reflectance. Injection moldable.

TYPICAL PROPERTY VALUES

Revision 20201125

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	60	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	61	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	6	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	120	%	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	98	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2670	MPa	ASTM D790
IMPACT			
Izod Impact, unnotched, 23°C	2130	J/m	ASTM D4812
Izod Impact, notched, 23°C	648	J/m	ASTM D256
Izod Impact, notched, -30°C	165	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	69	J	ASTM D3763
THERMAL			
Vicat Softening Temp, Rate B/50	142	°C	ASTM D1525
HDT, 0.45 MPa, 3.2 mm, unannealed	136	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	124	°C	ASTM D648
CTE, -40°C to 40°C, flow	6.E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	6.3E-05	1/°C	ASTM E831
PHYSICAL			
Specific Gravity	1.34	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 300°C/1.2 kgf	17	g/10 min	ASTM D1238
Density	1.31	g/cm³	ISO 1183
Water Absorption, (23°C/saturated)	0.35	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.15	%	ISO 62
FLAME CHARACTERISTICS			
UL Yellow Card Link	E121562-101123425	-	-
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	3 – 4	Hrs	
Drying Time (Cumulative)	48	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	280 – 305	°C	
Nozzle Temperature	275 – 300	°C	
Front - Zone 3 Temperature	280 – 305	°C	
Middle - Zone 2 Temperature	270 – 295	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Rear - Zone 1 Temperature	260 – 280	°C	
Mold Temperature	70 – 95	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.