

AF362H

Description

AF362H is an ABS product apply for injection molding. It has 2.5mm V-0 flame retardancy, high Thermal resistance, and good Thermal stability.

Key Features

Opaqueness, Flame Retardancy, Hot Stamping, Paintability, High Gloss, Bright White, Thermal Stability, Colorability

Application

Blood pressure monitor, oxygen concentrator, pulse monitor

Plant

China(Huizhou)

Properties	Condition	Method	Unit	AF362H
Physical				
Melt Flow Index	220°C, 10kg	ASTM D1238	g/10min	55
Mechanical				
Flexural Strength	23°C, 10mm/min, 6.4mm	ASTM D790	MPa	65
Flexural Modulus	23°C, 10mm/min, 6.4mm	ASTM D790	MPa	2400
Izod Impact Strength	Notched, 6.4mm, 23°C	ASTM D256	J/m	22
Rockwell Hardness	R-Scale	ASTM D785		103
Thermal				
Heat Deflection Temperature	Edgewise, 1.82MPa, 6.4mm, Unannealed	ASTM D648	°C	84

Note

Typical values can be used only for the purpose of selecting material, and there can be variation within normal tolerances for various colors. Values given should not be interpreted as specification and not be used for designing part or tool. All properties, except melt flow index are measured by injection molded specimens after 48 hours storage at 23°C, 50% relative humidity.

AF362H

Description

AF362H is an ABS product apply for injection molding. It has 2.5mm V-0 flame retardancy, high Thermal resistance, and good Thermal stability.

Key Features

Opaqueness, Flame Retardancy, Hot Stamping, Paintability, High Gloss, Bright White, Thermal Stability, Colorability

Application

Blood pressure monitor, oxygen concentrator, pulse monitor

Plant

China(Huizhou)

Processing Guide (Injection Molding)

Processing Parameters	Unit	Value
Drying Temperature	°C	80~90
Drying Time	hrs	3~4
Injection Temperature	°C	200~230
Mold Temperature	°C	40~60
Screw Speed	rpm	30~60

Note

Injection Temperature & Screw Speed are only mentioned as general guidelines. These may not apply or need adjustment in specific situations such as low shot sizes, thin wall molding and gas-assist molding.