

# AF366HF

Description

AF366HF is an ABS product apply for injection molding, with 1.5mm V-0 flame retardancy, high Thermal resistance, high flow and good Thermal stability.

Key Features

Opacity, High Flame Retardancy,  
Bright White

Application

Industrial electronic control boxes,  
purifiers, heaters

Plant

China(Huizhou)

| Properties                  | Condition                            | Method    | Unit | AF366HF |
|-----------------------------|--------------------------------------|-----------|------|---------|
| Mechanical                  |                                      |           |      |         |
| Tensile Strength at Yield   | 23°C, 50mm/min, 3.2mm                | ASTM D638 | MPa  | 42.5    |
| Flexural Strength           | 23°C, 10mm/min, 6.4mm                | ASTM D790 | MPa  | 62      |
| Flexural Modulus            | 23°C, 10mm/min, 6.4mm                | ASTM D790 | MPa  | 2200    |
| Izod Impact Strength        | Notched, 6.4mm, 23°C                 | ASTM D256 | J/m  | 20      |
| Rockwell Hardness           | R-Scale                              | ASTM D785 |      | 103     |
| Thermal                     |                                      |           |      |         |
| Heat Deflection Temperature | Edgewise, 1.82MPa, 6.4mm, Unannealed | ASTM D648 | °C   | 82      |

Note

Typical values can be used only for the purpose of selecting material, and there can be variation within normal tolerances for various colors.  
Values given should not be interpreted as specification and not be used for designing part or tool.  
All properties, except melt flow index are measured by injection molded specimens after 48 hours storage at 23°C, 50% relative humidity.

# AF366HF

### Description

AF366HF is an ABS product apply for injection molding, with 1.5mm V-0 flame retardancy, high Thermal resistance, high flow and good Thermal stability.

### Key Features

Opacity, High Flame Retardancy,  
Bright White

### Application

Industrial electronic control boxes,  
purifiers, heaters

### Plant

China(Huizhou)

### Processing Guide (Injection Molding)

| Processing Parameters | Unit | Value   |
|-----------------------|------|---------|
| Drying Temperature    | °C   | 70~80   |
| Drying Time           | hrs  | 3~4     |
| Injection Temperature | °C   | 200~230 |
| Mold Temperature      | °C   | 40~60   |
| Screw Speed           | rpm  | 30~60   |

### Note

Injection Temperature & Screw Speed are only mentioned as general guidelines.  
These may not apply or need adjustment in specific situations such as low shot sizes, thin wall molding and gas-assist molding.