

BM662

Blow Molding

Description

- Blow Molding, Heat Resistance

Applications

- Automotives Exterior Housing(Spoiler, Bumper Guard Etc)

Properties	Method	Unit	BM662
Physical			
Specific Gravity , 23°C	ISO 1183		1.05
Mold Shrinkage , 23°C, 3.2mm , 23°C	ISO 294-4	%	0.4 ~ 0.7
Melt Volume Rate , 220°C, 10kg	ISO 1133	cm ³ /10min	5
Mechanical			
Tensile Strength at Yield , 23°C, 50mm/min, 4mm	ISO 527	MPa	46
Tensile Elongation at Yield , 23°C, 50mm/min, 4mm	ISO 527	%, (Min)	5
Tensile Elongation at Break , 23°C, 50mm/min, 4mm	ISO 527	%, (Min)	10
Tensile Modulus , 23°C, 1mm/min, 4mm	ISO 527	MPa	1950
Flexural Strength , 23°C, 2mm/min, 4mm	ISO 178	MPa	73
Flexural Modulus , 23°C, 2mm/min, 4mm	ISO 178	MPa	2050
Izod Impact Strength , Notched, 4mm, 23°C	ISO 180/1A	kJ/m ²	25
Izod Impact Strength , Notched, 4mm, -30°C	ISO 180/1A	kJ/m ²	9
Charpy Impact Strength , 4mm, 23°C	ISO 179/1eA	kJ/m ²	23
Charpy Impact Strength , 4mm, -30°C	ISO 179/1eA	kJ/m ²	8
Rockwell Hardness , R-Scale	ISO 2039		101
Thermal			
HDT , Flatwise, 1.8MPa, 4mm, Unannealed	ISO 75	°C	87
VICAT , 50N, 50°C/h	ISO 306	°C	104

Updated Date : 17-Nov-17 Issued Date : 27-Sep-21

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.

BM662

Blow Molding

Description

- Blow Molding, Heat Resistance

Applications

- Automotives Exterior Housing(Spoiler, Bumper Guard Etc)

Note

Typical values can be used only for the purpose of selecting material, and there can be variation within normal tolerances for various colors. Values given should not be interpreted as specification and not be used for designing part or tool. All properties, except melt flow rate are measured by injection molded specimens after 48 hours storage at 23°C, 50% relative humidity.

Updated Date : 17-Nov-17 Issued Date : 27-Sep-21

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.