



Component - Plastics

File Number: E67171

LG CHEM LTD
20 YOIDO-DONG
YONGDUNGPO-GU
SEOUL, 150-721 Republic of Korea



SG175, SG175NS, SG175V

Acrylonitrile Butadiene Styrene (ABS), pellets

Flammability	Value	Test Method
Flame Rating		
1.5 mm, ALL	HB	UL 94
3.0 mm, ALL	HB	UL 94
3.0 mm, ALL	HB40	IEC 60695-11-10, -20
1.5 mm, ALL	HB75	IEC 60695-11-10, -20
Electrical	Value	Test Method
Hot-wire Ignition (HWI)		UL 746
1.5 mm	PLC 4	
3.0 mm	PLC 3	
High Amp Arc Ignition (HAI)		UL 746
1.5 mm	PLC 2	
3.0 mm	PLC 0	
Comparative Tracking Index (CTI)	PLC 0	UL 746
Dielectric Strength	28 kV/mm	ASTM D149
High Voltage Arc Tracking Rate (HVTR)	PLC 1	UL 746
Volume Resistivity	1.0E+16 ohms-cm	ASTM D257 IEC 60093
Arc Resistance	PLC 6	ASTM D495
Thermal	Value	Test Method
RTI Elec		UL 746
1.5 mm	60.0 °C	
3.0 mm	60.0 °C	
RTI Imp		UL 746
1.5 mm	60.0 °C	
3.0 mm	60.0 °C	
RTI Str		UL 746
1.5 mm	60.0 °C	
3.0 mm	60.0 °C	
Physical	Value	Test Method
Dimensional Stability	0.0 %	ASTM D1042 ISO 2796