



Property	Unit	Test Method	Test Condition	Transparent flame retardant
Model				AC3832
Melt Flow Index	g/10 min	ASTM D-1238	300°C×1.2kg	5
IZOD Impact Strength	kg-cm/cm	ASTM D-256	23°C, 3.2mm, Notched	75
Specific Gravity	-	ASTM D-792	23°C	1.2
Tensile Strength	kg/cm ²	ASTM D-638	23 °C, 50mm/min	710
Flexural Strength	kg/cm ²	ASTM D-790	23 °C, 2mm/min	1100
Flexural Modulus	kg/cm ²	ASTM D-790	23 °C, 2mm/min	22000
Rockwell Hardness	R-scale	ASTM D-785	23 °C	R-122
Heat Deflection Temperature	°C	ASTM D-648	Unannealed, 18.6kg/cm ² , 3.2mm, 120°C/h	128
Molding Shrinkage	%	ASTM D-955	-	0.5 ~ 0.7
Combustibility		UL-94	File No. E162823	v-0 1 mm 5VA 3 mm
Features	Transparency, Flame retardant, Low flow, UV resistance, Halogen free.			

All tests were run under laboratory conditions, ASTM, ISO testing procedures.
The data are intended as a general guide only.

Formosa Chemicals & Fibre Corp. Plastics Div.

TEL:+886-2-27122211 FAX: +886-2-27131649
Address: Building A2, No. 380, Section 6, Nanjing East Road, Neihu District, Taipei City 11470



www.fcfc-plastics.com