



Property	Unit	Test Method	Test Condition	Transparent flame retardant
Model				AC3854
Melt Flow Index	g/10 min	ISO 1133	300°C × 1.2kg	12
Charpy Impact Strength	kJ/m²	ISO 179	23°C, 4mm, Notched	70
Specific Gravity	-	ISO 1183	23°C	1.2
Tensile Strength	Mpa	ISO 527	23 °C, 50mm/min	70
Flexural Strength	Mpa	ISO 178	23 °C, 2mm/min	108
Flexural Modulus	Mpa	ISO 178	23 °C, 2mm/min	2155
Rockwell Hardness	R-scale	ISO 2039-2	23°C	R-122
Heat Deflection Temperature	°C	ISO 75/A	Unannealed, 1.8Mpa, 4mm, 120°C/h	128
Molding Shrinkage	%	ISO 2577	-	0.5 ~ 0.7
Combustibility		UL-94	File No. E162823	v-0 2.5 mm
Features	Transparency, Flame retardant, Mid-low flow, UV resistance, Halogen free.			

All tests were run under laboratory conditions, ASTM, ISO testing procedures.
The data are intended as a general guide only.

Formosa Chemicals & Fibre Corp. Plastics Div.

TEL:+886-2-27122211 FAX: +886-2-27131649
Address: Building A2, No. 380, Section 6, Nanjing East Road, Neihu District, Taipei City 11470



www.fcfc-plastics.com