



Property	Unit	Test Method	Test Condition	Ultra-low Temp resistance copolymer
Model				AC9144
Melt Flow Index	g/10 min	ISO 1133	300°C × 1.2kg	13
Specific Gravity	-	ISO 1183	23°C	1.18
Tensile Strength	Mpa	ISO 527	23 °C, 50mm/min	60
Tensile Strength	Mpa	ISO 527	23 °C, 20mm/min	0
Flexural Strength	Mpa	ISO 178	23 °C, 2mm/min	98
Flexural Modulus	Mpa	ISO 178	23 °C, 2mm/min	2060
Rockwell Hardness	R-scale	ISO 2039-2	23°C	R-120
Heat Deflection Temperature	°C	ISO 75/A	Unannealed, 1.8Mpa, 4mm, 120°C/h	120
Molding Shrinkage	%	ISO 2577	-	0.6 ~ 0.8
Combustibility		UL-94	File No. E162823	v-2 2 mm
Features	Translucency, Mid flow, Low temperature impact property, UV resistance,			

All tests were run under laboratory conditions, ASTM, ISO testing procedures.
The data are intended as a general guide only.

Formosa Chemicals & Fibre Corp. Plastics Div.

TEL: +886-2-27122211 FAX: +886-2-27131649
Address: Building A2, No. 380, Section 6, Nanjing East Road, Neihu District, Taipei City 11470



www.fcfc-plastics.com