

PC/ABS合金(合膠)



Formosa Chemical & Fibre Corporation

Property	Unit	Test Method	Test Condition	Self Extinguishing Grade
Model				AC3300
Melt Flow Index	g/10 min	ASTM D-1238	240°C × 5kg	42
Melt Flow Index	g/10 min	ASTM D-1238	260°C × 2.16kg	30
IZOD Impact Strength	kg-cm/cm	ASTM D-256	23°C, 3.2mm, Notched	29
Specific Gravity	-	ASTM D-792	23°C/23°C	1.18
Tensile Strength	kg/cm ²	ASTM D-638	23 °C	610
Flexural Strength	kg/cm ²	ASTM D-790	23 °C	1030
Flexural Modulus	kg/cm ²	ASTM D-790	23 °C	26000
Rockwell Hardness	R-scale	ASTM D-785	23 °C	R-118
Combustibility		UL-94	File No. E162823	v-0 1.2 ~ 1.8 mm 5VB 1.6 ~ 1.8 mm
Features	Flame retardant, Halogen free			

All tests were run under laboratory conditions, ASTM, ISO testing procedures.
The data are intended as a general guide only.

Formosa Chemicals & Fibre Corp. Plastics Div.

TEL: +886-2-27122211 FAX: +886-2-27131649
Address: Building A2, No. 380, Section 6, Nanjing East Road, Neihu District, Taipei City 11470



www.fcfc-plastics.com