

ABS樹脂



Formosa Chemical & Fibre Corporation

Property	Unit	Test Method	Test Condition	Jet Black Extrusion Grade
Model				AE10EP
Melt Flow Index	g/10 min	ASTM D-1238	220°C × 10kg	4.9
IZOD Impact Strength	kg-cm/cm	ASTM D-256	23 °C, 1/4", Notched	48
Specific Gravity	-	ASTM D-792	23°C	1.05
Tensile Strength	kg/cm ²	ASTM D-638	23 °C, 50mm/min	392
Flexural Strength	kg/cm ²	ASTM D-790	23 °C, 15mm/min	660
Flexural Modulus	kg/cm ²	ASTM D-790	23 °C, 15mm/min	21000
Features	MI(220°C×10kg): 5.7 Izod (ASTM,1/4"): 41 FM(ASTM): 20000 TS(ASTM): 370 Extrusion molding, Super high impact, High rigid			

All tests were run under laboratory conditions, ASTM, ISO testing procedures.
The data are intended as a general guide only.

Formosa Chemicals & Fibre Corp. Plastics Div.

TEL:+886-2-27122211 FAX: +886-2-27131649
Address: Building A2, No. 380, Section 6, Nanjing East Road, Neihu District, Taipei City 11470



www.fcfc-plastics.com