

ABS樹脂



Formosa Chemical & Fibre Corporation

Property	Unit	Test Method	Test Condition	20%GF Reinforced Grade
Model				AG20GF
Melt Flow Index	g/10 min	ASTM D-1238	220°C × 10kg	15
IZOD Impact Strength	kg-cm/cm	ASTM D-256	23 °C, 1/4", Notched	8.7
Tensile Strength	kg/cm ²	ASTM D-638	23 °C	1100
Flexural Strength	kg/cm ²	ASTM D-790	23 °C	69510
Features	MI(220°C×10kg):15 Izod (ASTM,1/4"):8.7 FM(ASTM):69510 TS(ASTM):1100 Dimensional stability High heat resistant			

All tests were run under laboratory conditions, ASTM, ISO testing procedures.
The data are intended as a general guide only.

Formosa Chemicals & Fibre Corp. Plastics Div.

TEL:+886-2-27122211 FAX: +886-2-27131649
Address: Building A2, No. 380, Section 6, Nanjing East Road, Neihu District, Taipei City 11470



www.fcfc-plastics.com