

Property	Unit	Test Method	Test Condition	Self Extinguishing Grade
Model				ANC120
Melt Flow Index	g/10 min	ASTM D-1238	200°C × 5kg	5.5
IZOD Impact Strength	kg-cm/cm	ASTM D-256	23 °C, 1/4", Notched	26
Specific Gravity	-	ASTM D-792	23°C/23°C	1.19
Tensile Strength	kg/cm ²	ASTM D-638	23 °C, 50mm/min	400
Flexural Strength	kg/cm ²	ASTM D-790	23 °C, 15mm/min	690
Flexural Strength	kg/cm ²	ASTM D-790	23 °C, 1.2mm/min	0
Flexural Modulus	kg/cm ²	ASTM D-790	23 °C, 15mm/min	23000
Rockwell Hardness	R-scale	ASTM D-785	23 °C	R-100
Vicat Softening Point	°C	ASTM D-1525	Annealed, 50N, 50°C/h	83
Heat Deflection Temperature	°C	ASTM D-648	Annealed, 1.8Mpa 1/4"厚, 120°C/h	84
Heat Deflection Temperature	°C	ASTM D-648	Unannealed, 1.8Mpa 1/4" 厚, 120°C/h	74
Combustibility		UL-94	File No. E162823	v-0 2.3 ~ 3 mm 5VB 2.3 ~ 3 mm
Features	Flame retardant			

All tests were run under laboratory conditions, ASTM, ISO testing procedures.
The data are intended as a general guide only.

Formosa Chemicals & Fibre Corp. Plastics Div.

TEL: +886-2-27122211 FAX: +886-2-27131649
Address: Building A2, No. 380, Section 6, Nanjing East Road, Neihu District, Taipei City 11470

