



單聚物PP樹脂

Formosa Chemical & Fibre Corporation

Property	Unit	Test Method	Test Condition	Injection Molding
Model				K1011AG
Melt Flow Index	g/10 min	ISO 1133	230℃ × 2.16kg	15
IZOD Impact Strength	kJ/m²	ISO 180	23 °C, 1/8", Notched	35
IZOD Impact Strength	kJ/m²	ISO 180	23 °C, 4mm, Notched	35
Specific Gravity	-	ISO 1183	23°C/23°C	0.9
Tensile Strength	Mpa	ISO 527	23 °C, 50mm/min	37
Tensile Elongation at break	%	ISO 527	23 °C, 50mm/min	>200
Flexural Modulus	Mpa	ISO 178	23 °C	1617
Rockwell Hardness	R-scale	ISO 2039-2	23°C	R-107
Heat Deflection Temperature	℃	ISO 75/A	Unannealed, 0.455Mpa 1/4" 厚, 120°C/h	125
Molding Shrinkage	%	FCFC Method	23 °C	1.4 ~ 1.8
Combustibility		UL-94	File No. E162823	HB 1.5 ~ 3 mm
Features	Long term heat resistance,High stiffness,Good luster			

All tests were run under laboratory conditions, ASTM, ISO testing procedures.
The data are intended as a general guide only.

Formosa Chemicals & Fibre Corp. Plastics Div.

TEL:+886-2-27122211 FAX: +886-2-27131649
Address: Building A2, No. 380, Section 6, Nanjing East Road, Neihu District, Taipei City 11470



www.fcfc-plastics.com