



單聚物PP樹脂

Formosa Chemical & Fibre Corporation

Property	Unit	Test Method	Test Condition	Extrusion & Blow Molding
Model				T1202
Melt Flow Index	g/10 min	ISO 1133	230°C × 2.16kg	1.6
IZOD Impact Strength	kJ/m ²	ISO 180	23 °C, 1/8", Notched	44
IZOD Impact Strength	kJ/m ²	ISO 180	23 °C, 4mm, Notched	44
Features	high stiffness, heat resistance, clarity MI(230°C×2.16kg):1.6 Izod(ASTM,1/8"):4.5 FM(ASTM):18000 TS(ASTM):380			

All tests were run under laboratory conditions, ASTM, ISO testing procedures.
The data are intended as a general guide only.

Formosa Chemicals & Fibre Corp. Plastics Div.

TEL:+886-2-27122211 FAX: +886-2-27131649
Address: Building A2, No. 380, Section 6, Nanjing East Road, Neihu District, Taipei City 11470



www.fcfc-plastics.com