



Property	Unit	Test Method	Test Condition	GPPS (General Purpose PS)
Model				GP5350
Melt Flow Index	g/10 min	ASTM D-1238	200°C × 5kg	4.5
IZOD Impact Strength	kg-cm/cm	ASTM D-256	23 °C, 1/4", Notched	1.8
Tensile Strength	kg/cm ²	ASTM D-638	23 °C, 5mm/min	450
Tensile Modulus	kg/cm ²	ASTM D-638	23 °C, 1mm/min	32000
Tensile Elongation	%	ASTM D-638	23 °C, 5mm/min	2
Flexural Strength	kg/cm ²	ASTM D-790	23 °C, 1.2mm/min	900
Flexural Modulus	kg/cm ²	ASTM D-790	23 °C, 1.2mm/min	32000
Vicat Softening Point	°C	ASTM D-1525	Annealed 80°C*2hr 1/8" , 10N 50°C/h	98
Reidual Monomer	ppm max		-	700
Heat Deflection Temperature	°C	ASTM D-648	Annealed 80°C*2hr, 120°C/h 1.8Mpa 1/8"	90
Combustibility		UL-94	File No. E162823	HB 1.5 ~ 1.7 mm
Features	High heat resistance			

All tests were run under laboratory conditions, ASTM, ISO testing procedures.
The data are intended as a general guide only.

Formosa Chemicals & Fibre Corp. Plastics Div.

TEL:+886-2-27122211 FAX: +886-2-27131649
Address: Building A2, No. 380, Section 6, Nanjing East Road, Neihu District, Taipei City 11470



www.fcfc-plastics.com