

VALOX™ FR RESINS 771

REGION AMERICAS

DESCRIPTION

VALOX 771 is a 35% mineral/glass filled, flame retardant Polybutylene Terephthalate (PBT) injection moldable grade. It has excellent chemical resistance and a UL94V0@0.75 flame rating and 5VA@2.0mm. This grade also has a CTI of 0 and is a good candidate for applications that may see electrical arcing.

TYPICAL PROPERTY VALUES

Revision 20241105

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	72	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	2.3	%	ASTM D638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	110	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	5860	MPa	ASTM D790
IMPACT			
Izod Impact, unnotched, 23°C	390	J/m	ASTM D4812
Izod Impact, notched, 23°C	42	J/m	ASTM D256
THERMAL			
HDT, 0.45 MPa, 6.4 mm, unannealed	217	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	196	°C	ASTM D648
Ball Pressure Test			
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Ball Pressure Test, 175°C +/- 2°C	PASSES	-	IEC 60695-10-2
Relative Temp Index, Elec	140	°C	UL 746B
Relative Temp Index, Mech w/impact	125	°C	UL 746B
Relative Temp Index, Mech w/o impact	140	°C	UL 746B
PHYSICAL			
Specific Gravity	1.7	-	ASTM D792
Mold Shrinkage on Tensile Bar, flow	0.65 – 0.85	%	SABIC method
Mold Shrinkage on Tensile Bar, xflow	1 – 1.2	%	SABIC method
ELECTRICAL			
Arc Resistance, Tungsten {PLC}	4	PLC Code	ASTM D495
Hot Wire Ignition {PLC}	0	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	0	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	0	PLC Code	UL 746A
Comparative Tracking Index	600	V	IEC 60112
Volume Resistivity	>1.E+15	Ω.cm	ASTM D257
Volume Resistivity	>1.E+15	Ω.cm	IEC 60093
Comparative Tracking Index (UL) {PLC}	0	PLC Code	UL 746A
FLAME CHARACTERISTICS			
UL Yellow Card Link	E121562-220821	-	-
UL Recognized, 94V-2 Flame Class Rating	0.62	mm	UL 94
UL Recognized, 94V-0 Flame Class Rating	0.75	mm	UL 94

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
UL Recognized, 94-5VA Flame Class Rating	2.0	mm	UL 94
Glow Wire Flammability Index 960°C, passes at	1	mm	IEC 60695-2-12
Glow Wire Flammability Index 960°C, passes at, by VDE	3	mm	IEC 60695-2-12
Glow Wire Ignitability Temperature, 1.0 mm	750	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 3.0 mm	800	°C	IEC 60695-2-13
INJECTION MOLDING			
Drying Temperature	110 – 120	°C	
Drying Time	3 – 4	Hrs	
Drying Time (Cumulative)	12	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	255 – 275	°C	
Nozzle Temperature	255 – 270	°C	
Front - Zone 3 Temperature	255 – 265	°C	
Middle - Zone 2 Temperature	250 – 260	°C	
Rear - Zone 1 Temperature	245 – 255	°C	
Hopper Temperature	40 – 60	°C	
Mold Temperature	40 – 100	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	50 – 80	rpm	
Shot to Cylinder Size	40 – 80	%	
Vent Depth	0.025 – 0.038	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.